

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

SPECIFICATION

INVENTION: **WAVE GUIDE PLATE AND PROCESS FOR ITS PRODUCTION AND
MICROTITRE PLATE**

INVENTOR: **Bernd MAISENHÖLDER**
Citizenship: German
Post Office Address/ Schlindersteig 1
CH-8006, Zürich
Residence: Switzerland

INVENTOR: **Johannes EDLINGER**
Citizenship: Austrian
Post Office Address/ Letzestrasse 1
A-6820 Frastanz
Residence: Austria

INVENTOR: **Clause HEINE**
Citizenship: German
Post Office Address/ Rabengasse 10
CH-700 Chur
Residence: Switzerland

ATTORNEYS: **CROWELL & MORING L.L.P.**
Suite 700
1200 G Street, N.W
Washington, D.C. 20005
Telephone No.: (202) 628-8800
Facsimile No.: (202) 628-8844

WAVEGUIDE PLATE AND PROCESS FOR ITS PRODUCTION AND MICROTITRE PLATE

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation-in-part of U.S. application Serial No. 09/497,129 filed on February 3, 2000.

BACKGROUND OF THE INVENTION

[0002] The invention relates to a waveguide plate and a process for its production and a microtitre plate comprising such a waveguide plate and as used, for example, for analytical purposes in the biochemical and medical sector, as well as a sensor platform based on a waveguide plate, an evanescent field sensor plate, according to the invention as well as arrangements of sample compartments, with a waveguide plate or a sensor platform according to the invention as a boundary surface of said arrangement of sample compartments. The invention also relates to an optical coupler and a device for monitoring such a coupler.

[0003] The process according to the invention is suitable for producing optical elements with grating structures. Evanescent field sensor plates and microtitre plates produced according to the process can be used in chemical and biomolecular analyses. Optical couplers have applications in communications technology, and more particularly in data transmission via fibre networks. A potential application of a particular coupler according to the invention is in a device for monitoring the wavelength of laser light in a fiber network.

[0004] EP-A-0 602 829 discloses a process for producing a grating structure on a substrate, for example for a DBR semiconductor laser, in which first a phase mask is produced and then the substrate, e.g.. InP, is exposed at the Lithrow angle, through the phase mask. The exposure can be effected by means of an Hg-Xe arc lamp having a light source diameter of 0.25 mm, three lines around 365 nm wavelength being filtered out. The substrate is located close to the phase mask, i.e. at a distance of not more than 10 microns.

[0005] To produce the phase mask, a quartz substrate is covered with three layers, a photoresist layer, a thin germanium layer and finally a layer of a resist sensitive to electron beams. The uppermost layer is then structured by inscribing by means of electron beams, developing the uppermost layer and removing the unexposed parts. The structure is transferred to the layers underneath by reactive ion etching, initially with CF₃Br and then with O₂, and finally to the quartz substrate itself by a further step of reactive ion etching, whereupon the residues of the layers are removed. The grating constant may be, for example, between 190 nm and 250 nm. The phase mask may be several centimeters long and the grating may extend over its entire length. However, the length of the lines is, as a rule, only 5-20 microns. Greater lengths are possible but require very long processing times. In practice, gratings of more than 1 mm² can hardly be produced with reasonable effort and good accuracy. In particular, stitching errors during inscribing by means of electron beams cannot be avoided.

[0006] From US-A-5 675 691 a plate is known on which coupling

gratings are produced by applying a layer of TiO_2 , Ta_2O_5 , HfO_2 , Y_2O_3 , Al_2O_3 , Nb_2O_5 , nitride or oxynitride of Al, Si or Hf to a substrate of glass, in particular quartz glass, ceramic, or predominantly organic material. It is being possible to provide a 20 nm thick intermediate layer, e.g. of SiO_2 , and to structure it by ablation or modification of the refractive index by means of exposure to two superimposed beams of an excimer laser or to a beam modified by a mask. Instead, it is also possible to structure an intermediate layer, e.g. of TiO_2 , in which the ablation barrier is lower and which is applied either to the layer or directly to the substrate and, in the latter case, is superimposed by the layer after structuring. The grating periods are, for example, 375 nm or 440 nm. The grating surface area is freely selectable and may be, for example, 1 mm x 1 mm or 8 mm x 8 mm.

[0007] From US-A-5 822 472 an evanescent field sensor plate for chemical analyses is known which bears a 40 nm to 160 nm thick layer of TiO_2 , ZnO , Nb_2O_5 , Ta_2O_5 , HfO_2 or ZrO_2 on a support of plastic, glass or quartz. An intermediate layer of nonluminescent material with a low refractive index, e.g., quartz having a thickness of 100 nm, for example, which at the same time serves as an adhesion promoter, may be arranged in between. An input coupling grating and an output coupling grating are provided which are created by known photolithographic or holographic and etching methods, either in the support or in the layer, and have a grating period of between 200 nm and 1000 nm. The gratings may have dimensions of 2 mm (parallel to the lines) x 4 mm, with a total surface area of the wave-guide plate of 12 mm x 20 mm.

[0008] From J. Duebendorfer and R.E. Kunz: "Compact integrated

optical immunosensor using replicated chirped coupling grating sensor chips", Applied Optics, 37/10 (1st April 1998), a further evanescent field sensor plate comprising a polycarbonate support plate is known into which a modulated input coupling grating having a grating period varying between 420 nm and 422.8 nm and an output coupling grating having a grating period varying between 595.1 nm and 600.8 nm were embossed. Thereafter, a TiO₂ layer having a thickness of 137 nm and a refractive index of 2.346 was applied by means of low-temperature DC magnetron sputtering, and finally the evanescent field sensor plate was silanised. The input coupling angle is about -9.5° and the output coupling angle is about 22.5°.

[0009] From US-A-5 738 825 a microtitre plate can be obtained which has a 20 nm to 1000 nm, preferably 30 nm to 500 nm thick layer of TiO₂, Ta₂O₅, HfO₂, ZrO₂, SiO₂, Si₃N₄, Al₂O₃, Nb₂O₅ nitride or oxynitride of Al, Si or Hf applied to its bottom surface, this layer being covered by a plastic layer. Input and output coupling gratings are mounted underneath each cavity. The gratings have a grating period between 330 nm and 1000 nm, in particular about 400 nm to 800 nm, and are produced by lithographic or mechanical methods.

[0010] From CH-A-688 165 a wave-guide plate comprising a substrate of plastic, e.g. polycarbonate, is known whose surface was structured mechanically - by deep drawing, embossing or during its injection moulding - and in particular provided with a coupling grating, and bears a layer of TiO₂, Ta₂O₅, ZrO₂, Al₂O₃, SiO₂-TiO₂, HfO₂, Y₂O₃, Nb₂O₅, silicon nitride, oxynitride, SiO_xN_y, HfO_xN_y, AlO_xN_y, TiO_xN_y, MgF₂ or CaF₂ applied by

a PVD method. To reduce the attenuation losses, an approximately 20 nm thick intermediate layer applied to the substrate prior to the layer and comprising an inorganic dielectric material such as SiO₂ is provided which at the same time serves as an adhesion promoter.

[0011] All plates described above are produced by processes with which no satisfactory uniformity of the coupling grating can be achieved, so that the coupling angle varies relatively widely. Consequently, the relative angular position of the exposure unit and plate must be optimised laboriously in each step when the plate is to be used as a waveguide or an evanescent field sensor plate. The filter characteristics are unsatisfactory and not sufficient, for instance, for selectively filtering a particular wavelength from a group of very closely spaced wavelengths, when the plate is used as an optical coupler in communications technology. Some of the processes described are also very laborious or do not allow very large numbers of pieces of constant quality to be made.

SUMMARY OF THE INVENTION

[0012] It is the object of the invention to provide a waveguide plate which permits feasible rapid analysis with little effort. In addition, it is intended to provide a microtitre plate based on such a waveguide plate. As a result of the limits which are narrow also with large grating lengths and within which the coupling angle varies, it is possible simultaneously to expose and to read out larger parts of the waveguide plate or microtitre plate. Successive exposures of different parts of the waveguide plate or microtitre plate are also simplified

since reoptimization of the relative angle between it and the exposure unit is not required or in any case very easy.

[0013] Furthermore, it is the object of the invention to provide a process for producing a waveguide plate according to the invention, which permits the creation of large gratings in particular having long parallel lines with great precision, provides freedom of design with regard to the arrangement of the gratings and is simple and economical. The process according to the invention furthermore permits the production of large series of waveguide plates of constant quality and having optical properties, such as coupling efficiencies and in particular coupling angles, which are within narrow limits. The process according to the invention also permits the production of large series of optical elements of constant quality and with optical properties such as coupling efficiencies and, in particular, coupling angles which are constant within narrow limits.

[0014] The process according to the invention furthermore permits the production of large series of optical elements of constant quality and with optical properties such as coupling efficiencies and, in particular, coupling angles which are constant within narrow limits.

[0015] It is also an object of the invention to provide a sensor platform and an arrangement of sample compartments, based on a waveguide plate according to the invention

[0016] Additionally, a highly precise optical element is to be

provided such as can be produced by the process according to the invention. In particular, the optical element can be formed as a waveguide plate or an evanescent field sensor plate or as a microtitre plate based on such a plate. In view of the narrow limits within which, even in long gratings, the coupling angle varies, it is possible to simultaneously illuminate and read out larger parts of the waveguide plate or evanescent field sensor plate or microtitre plate. Successive exposure of different parts of the waveguide plate or the evanescent field sensor plate or microtitre plate is also simplified since reoptimization of the relative angular position of this plate and the exposing unit is not required or in any case greatly simplified.

[0017] The optical element can also be formed as an optical coupler for communications technology. In this case, the high precision present even in large grating structures guarantees excellent filter characteristics, and particularly a very-narrow-band selection of individual wavelengths, so that, for instance, a wavelength multiplexing involving very closely spaced wavelengths is possible, which raises the transmission capacity.

[0018] Other objects, advantages and novel features of the present invention will become apparent from the following detailed description of the invention when considered in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0019] Fig. 1 shows a plan view of a waveguide plate according to

the invention which can be an evanescent field sensor plate having an attachment or headpiece which is indicated by a dashed line and supplements it to form an arrangement of sample compartments or a complete microtitre plate with sample compartments or a complete waveguide plate system,

[0020] Fig. 2 shows a section along II-II in Fig. 1,

[0021] Fig. 3 schematically shown the use of an arrangement of sample compartments or of a complete microtitre plate with a waveguide plate or a sensor platform (evanescent field sensor plate) according to the invention, as a boundary surface being part of the cavities of the sample compartments or the microtitre plate,

[0022] Fig. 4a-e show different steps in the production of a waveguide plate according to the invention,

[0023] Fig. 5 schematically shows the setup used for exposing the photoresist layer during the production of the waveguide plate according to the invention,

[0024] Fig. 6 shows the phase mask and the glass substrate with the photoresist layer under exposure and

[0025] Fig. 7a-g show different steps in the production of a phase mask for the production of a waveguide plate according to the invention.

[0026] Fig. 8a schematically shows a plan view of a first embodiment of an optical coupler for communications technology according to the invention,

[0027] Fig. 8b schematically shows a central section through the coupler according to Fig. 8a,

[0028] Fig. 9a schematically shows the reflectivity of the coupler according to the first embodiment,

[0029] Fig. 9b-d shows diagrams showing the selection of a wavelength by the coupler according to the first embodiment,

[0030] Fig. 10 shows an arrangement with a coupler according to the first embodiment,

[0021] Fig. 11a schematically shows a plan view of a second embodiment of an optical coupler for communications technology according to the invention,

[0032] Fig. 11b schematically shows a central section through the coupler according to Fig. 11a,

[0033] Fig. 12 shows an arrangement with a coupler according to the second embodiment,

[0034] Fig. 13a schematically shows a plan view of a third

embodiment of an optical coupler for communications technology according to the invention,

[0035] Fig. 13b schematically shows a central section through the coupler according to Fig. 13a,

[0036] Fig. 14 shows a device for monitoring and stabilizing the wavelength of a light beam emitted by a laser which comprises a coupler according to the third embodiment, and

[0037] Fig. 15 shows the transmissivity of the coupler according to the third embodiment as a function of its position on the coupling grating at different wavelengths.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0038] The process according to the invention will first be explained in more detail in connection with an evanescent field sensor plate, respectively a waveguide plate and its production. Here, an evanescent field sensor plate is understood as a waveguide plate making it possible, by illumination of one part of the surface, to create an evanescent field in which a sample to be analyzed may be arranged. Therefore, evanescent field sensor plates may for example serve the purposes of chemical analysis. Evanescent fields are nonradiating electromagnetic fields which fall off and vanish with increasing distance from the scattering surface at which they are generated. Such fields can arise in connection with spatial modulations at the electric field in the plane having periodicities smaller than one wavelength.

The best-known example of such a modulation occurs at an interface between a dielectric and air when a light beam coming from the side of the dielectric has an angle of incidence larger than the critical angle.

[0039] Evanescent field sensor plates respectively waveguide plates have a transparent wave-guide layer from which the evanescent light leaves their surface, and interacts with bound molecules present there, for instance exciting their luminescence.

[0040] The plate according to the invention consists (Fig. 1, 2, the diagrams are schematic and not to scale) of a glass substrate 1, for example of AF 45 from Schott DESAG, having dimensions of 102 mm x 72 mm and a thickness of 0.7 mm, which carries on one side a 150 nm thick waveguide layer 2 comprising Ta2O5. Its refractive index at a wavelength of 633 nm is 2.11.

[0041] A plurality of parallel coupling grating strips 3 which are spaced apart and extend in parallel lines each over the entire width of the waveguide plate are present on the surface carrying the waveguide layer 2. The width of each of the coupling grating strips 3 is 0.5 mm. The grating period is $\Lambda = 360$ nm, the groove/land ratio is about 1:1, and the grating depth is about 20 nm. The parameters defining the grating are each maintained very accurately over the total length of the coupling grating strip. Consequently, changes in the coupling angle θ at which a light beam directed from below through the glass substrate 1 at the coupling grating strip 3, in particular having a wavelength of about 633 nm, is coupled into the waveguide layer 2 with maximum coupling

efficiency remains within very narrow limits. Along the lines of a coupling grating strip 3, the angle changes by not more than $0.05^\circ/\text{cm}$. On the whole waveguide plate, the deviation of the coupling angle from the mean value, which is 2.31° in the described example, is below 0.15° .

[0042] The surface of layer 2 is preferably provided with a coating consisting of an adhesion promoter layer, preferably of at least one chemical compound selected from the group of silanes, epoxides, functionalized, charged or polar polymers and self-organizing passive or functionalized mono-or multi-layers, and on top of it immobilized biological or biochemical or synthetic molecular recognition elements such as nucleic acids, antibodies, antigens, membrane receptors, and their ligands.

[0043] As shown in Fig. 3 and indicated in Fig. 1, the waveguide plate or evanescent field sensor plate is supplemented by a honeycomb-like attachment 4 of plastic to give an arrangement of sample compartments, preferably with the footprint of an industrial standard plate or to give a microtitre plate for use for chemical analysis, in particular of biological substances. The attachment has a cover plate 5 which is perforated by round openings 6 having a diameter of, for example, about 8 mm arranged in a regular array. At each of the openings 6, a tube section 7 which is open at the bottom, laterally bounds a cavity 8 and is tightly connected, for example adhesively bonded, at the lower end to the waveguide or evanescent field sensor plate 2.

[0044] On the other hand, in order to provide a waveguide plate

enabling the conduction of fast analysis with low effort, a waveguide plate is provided, according to the invention, with a plate-like glass substrate (1), carrying a waveguiding layer (2), with at least one coupling grating on the surface carrying the waveguiding layer (2), which coupling grating is formed as a grating of lines with a period between 150 nm and 1000 nm, the extension of said grating being at least 5 cm with lines parallel to one another, wherein the coupling angle (θ) varies by not more than $0.1^\circ/\text{cm}$ along a line of said grating and wherein the absolute value of the deviation of the coupling angle (θ) on said waveguide plate, from a predefined desired value, does not exceed 0.5° .

09560
09561
09562
09563
09564
09565
09566
09567
09568
09569
09570
09571
09572
09573
09574
09575
09576
09577
09578
09579
09580
09581
09582
09583
09584
09585
09586
09587
09588
09589
09590
09591
09592
09593
09594
09595
09596
09597
09598
09599
09600
09601
09602
09603
09604
09605
09606
09607
09608
09609
09610
09611
09612
09613
09614
09615
09616
09617
09618
09619
09620
09621
09622
09623
09624
09625
09626
09627
09628
09629
09630
09631
09632
09633
09634
09635
09636
09637
09638
09639
09640
09641
09642
09643
09644
09645
09646
09647
09648
09649
09650
09651
09652
09653
09654
09655
09656
09657
09658
09659
09660
09661
09662
09663
09664
09665
09666
09667
09668
09669
09670
09671
09672
09673
09674
09675
09676
09677
09678
09679
09680
09681
09682
09683
09684
09685
09686
09687
09688
09689
09690
09691
09692
09693
09694
09695
09696
09697
09698
09699
09700
09701
09702
09703
09704
09705
09706
09707
09708
09709
09710
09711
09712
09713
09714
09715
09716
09717
09718
09719
09720
09721
09722
09723
09724
09725
09726
09727
09728
09729
09730
09731
09732
09733
09734
09735
09736
09737
09738
09739
09740
09741
09742
09743
09744
09745
09746
09747
09748
09749
09750
09751
09752
09753
09754
09755
09756
09757
09758
09759
09760
09761
09762
09763
09764
09765
09766
09767
09768
09769
09770
09771
09772
09773
09774
09775
09776
09777
09778
09779
09780
09781
09782
09783
09784
09785
09786
09787
09788
09789
09790
09791
09792
09793
09794
09795
09796
09797
09798
09799
09800
09801
09802
09803
09804
09805
09806
09807
09808
09809
09810
09811
09812
09813
09814
09815
09816
09817
09818
09819
09820
09821
09822
09823
09824
09825
09826
09827
09828
09829
09830
09831
09832
09833
09834
09835
09836
09837
09838
09839
09840
09841
09842
09843
09844
09845
09846
09847
09848
09849
09850
09851
09852
09853
09854
09855
09856
09857
09858
09859
09860
09861
09862
09863
09864
09865
09866
09867
09868
09869
09870
09871
09872
09873
09874
09875
09876
09877
09878
09879
09880
09881
09882
09883
09884
09885
09886
09887
09888
09889
09890
09891
09892
09893
09894
09895
09896
09897
09898
09899
09900
09901
09902
09903
09904
09905
09906
09907
09908
09909
09910
09911
09912
09913
09914
09915
09916
09917
09918
09919
09920
09921
09922
09923
09924
09925
09926
09927
09928
09929
09930
09931
09932
09933
09934
09935
09936
09937
09938
09939
09940
09941
09942
09943
09944
09945
09946
09947
09948
09949
09950
09951
09952
09953
09954
09955
09956
09957
09958
09959
09960
09961
09962
09963
09964
09965
09966
09967
09968
09969
09970
09971
09972
09973
09974
09975
09976
09977
09978
09979
09980
09981
09982
09983
09984
09985
09986
09987
09988
09989
09990
09991
09992
09993
09994
09995
09996
09997
09998
09999
10000
10001
10002
10003
10004
10005
10006
10007
10008
10009
10010
10011
10012
10013
10014
10015
10016
10017
10018
10019
10020
10021
10022
10023
10024
10025
10026
10027
10028
10029
10030
10031
10032
10033
10034
10035
10036
10037
10038
10039
10040
10041
10042
10043
10044
10045
10046
10047
10048
10049
10050
10051
10052
10053
10054
10055
10056
10057
10058
10059
10060
10061
10062
10063
10064
10065
10066
10067
10068
10069
10070
10071
10072
10073
10074
10075
10076
10077
10078
10079
10080
10081
10082
10083
10084
10085
10086
10087
10088
10089
10090
10091
10092
10093
10094
10095
10096
10097
10098
10099
10100
10101
10102
10103
10104
10105
10106
10107
10108
10109
10110
10111
10112
10113
10114
10115
10116
10117
10118
10119
10120
10121
10122
10123
10124
10125
10126
10127
10128
10129
10130
10131
10132
10133
10134
10135
10136
10137
10138
10139
10140
10141
10142
10143
10144
10145
10146
10147
10148
10149
10150
10151
10152
10153
10154
10155
10156
10157
10158
10159
10160
10161
10162
10163
10164
10165
10166
10167
10168
10169
10170
10171
10172
10173
10174
10175
10176
10177
10178
10179
10180
10181
10182
10183
10184
10185
10186
10187
10188
10189
10190
10191
10192
10193
10194
10195
10196
10197
10198
10199
10200
10201
10202
10203
10204
10205
10206
10207
10208
10209
10210
10211
10212
10213
10214
10215
10216
10217
10218
10219
10220
10221
10222
10223
10224
10225
10226
10227
10228
10229
10230
10231
10232
10233
10234
10235
10236
10237
10238
10239
10240
10241
10242
10243
10244
10245
10246
10247
10248
10249
10250
10251
10252
10253
10254
10255
10256
10257
10258
10259
10260
10261
10262
10263
10264
10265
10266
10267
10268
10269
10270
10271
10272
10273
10274
10275
10276
10277
10278
10279
10280
10281
10282
10283
10284
10285
10286
10287
10288
10289
10290
10291
10292
10293
10294
10295
10296
10297
10298
10299
10300
10301
10302
10303
10304
10305
10306
10307
10308
10309
10310
10311
10312
10313
10314
10315
10316
10317
10318
10319
10320
10321
10322
10323
10324
10325
10326
10327
10328
10329
10330
10331
10332
10333
10334
10335
10336
10337
10338
10339
10340
10341
10342
10343
10344
10345
10346
10347
10348
10349
10350
10351
10352
10353
10354
10355
10356
10357
10358
10359
10360
10361
10362
10363
10364
10365
10366
10367
10368
10369
10370
10371
10372
10373
10374
10375
10376
10377
10378
10379
10380
10381
10382
10383
10384
10385
10386
10387
10388
10389
10390
10391
10392
10393
10394
10395
10396
10397
10398
10399
10400
10401
10402
10403
10404
10405
10406
10407
10408
10409
10410
10411
10412
10413
10414
10415
10416
10417
10418
10419
10420
10421
10422
10423
10424
10425
10426
10427
10428
10429
10430
10431
10432
10433
10434
10435
10436
10437
10438
10439
10440
10441
10442
10443
10444
10445
10446
10447
10448
10449
10450
10451
10452
10453
10454
10455
10456
10457
10458
10459
10460
10461
10462
10463
10464
10465
10466
10467
10468
10469
10470
10471
10472
10473
10474
10475
10476
10477
10478
10479
10480
10481
10482
10483
10484
10485
10486
10487
10488
10489
10490
10491
10492
10493
10494
10495
10496
10497
10498
10499
10500
10501
10502
10503
10504
10505
10506
10507
10508
10509
10510
10511
10512
10513
10514
10515
10516
10517
10518
10519
10520
10521
10522
10523
10524
10525
10526
10527
10528
10529
10530
10531
10532
10533
10534
10535
10536
10537
10538
10539
10540
10541
10542
10543
10544
10545
10546
10547
10548
10549
10550
10551
10552
10553
10554
10555
10556
10557
10558
10559
10560
10561
10562
10563
10564
10565
10566
10567
10568
10569
10570
10571
10572
10573
10574
10575
10576
10577
10578
10579
10580
10581
10582
10583
10584
10585
10586
10587
10588
10589
10590
10591
10592
10593
10594
10595
10596
10597
10598
10599
10600
10601
10602
10603
10604
10605
10606
10607
10608
10609
10610
10611
10612
10613
10614
10615
10616
10617
10618
10619
10620
10621
10622
10623
10624
10625
10626
10627
10628
10629
10630
10631
10632
10633
10634
10635
10636
10637
10638
10639
10640
10641
10642
10643
10644
10645
10646
10647
10648
10649
10650
10651
10652
10653
10654
10655
10656
10657
10658
10659
10660
10661
10662
10663
10664
10665
10666
10667
10668
10669
10670
10671
10672
10673
10674
10675
10676
10677
10678
10679
10680
10681
10682
10683
10684
10685
10686
10687
10688
10689
10690
10691
10692
10693
10694
10695
10696
10697
10698
10699
10700
10701
10702
10703
10704
10705
10706
10707
10708
10709
10710
10711
10712
10713
10714
10715
10716
10717
10718
10719
10720
10721
10722
10723
10724
10725
10726
10727
10728
10729
10730
10731
10732
10733
10734
10735
10736
10737
10738
10739
10740
10741
10742
10743
10744
10745
10746
10747
10748
10749
10750
10751
10752
10753
10754
10755
10756
10757
10758
10759
10760
10761
10762
10763
10764
10765
10766
10767
10768
10769
10770
10771
10772
10773
10774
10775
10776
10777
10778
10779
10780
10781
10782
10783
10784
10785
10786
10787
10788
10789
10790
10791
10792
10793
10794
10795
10796
10797
10798
10799
10800
10801
10802
10803
10804
10805
10806
10807
10808
10809
10810
10811
10812
10813
10814
10815
10816
10817
10818
10819
10820
10821
10822
10823
10824
10825
10826
10827
10828
10829
10830
10831
10832
10833
10834
10835
10836
10837
10838
10839
10840
10841
10842
10843
10844
10845
10846
10847
10848
10849
10850
10851
10852
10853
10854
10855
10856
10857
10858
10859
10860
10861
10862
10863
10864
10865
10866
10867
10868
10869
10870
10871
10872
10873
10874
10875
10876
10877
10878
10879
10880
10881
10882
10883
10884
10885
10886
10887
10888
10889
10890
10891
10892
10893
10894
10895
10896
10897
10898
10899
10900
10901
10902
10903
10904
10905
10906
10907
10908
10909
10910
10911
10912
10913
10914
10915
10916
10917
10918
10919
10920
10921
10922
10923
10924
10925
10926
10927
10928
10929
10930
10931
10932
10933
10934
10935
10936
10937
10938
10939
10940
10941
10942
10943
10944
10945
10946
10947
10948
10949
10950
10951
10952
10953
10954
10955
10956
10957
10958
10959
10960
10961
10962
10963
10964
10965
10966
10967
10968
10969
10970
10971
10972
10973
10974
10975
10976
10977
10978
10979
10980
10981
10982
10983
10984
10985
10986
10987
10988
10989
10990
10991
10992
10993
10994
10995
10996
10997
10998
10999
11000
11001
11002
11003
11004
11005
11006
11007
11008
11009
11010
11011
11012
11013
11014
11015
11016
11017
11018
11019
11020
11021
11022
11023
11024
11025
11026
11027
11028
11029
11030
11031
11032
11033
11034
11035
11036
11037
11038
11039
11040
11041
11042
11043
11044
11045
11046
11047
11048
11049
11050
11051
11052
11053
11054
11055
11056
11057
11058
11059
11060
11061
11062
11063
11064
11065
11066
11067
11068
11069
11070
11071
11072
11073
11074
11075
11076
11077
11078
11079
11080
11081
11082
11083
11084
11085
11086
11087
11088
11089
11090
11091
11092
11093
11094
11095
11096
11097
11098
11099
11100
11101
11102
11103
11104
11105
11106
11107
11108
11109
11110
11111
11112
11113
11114
11115
11116
11117
11118
11119
11120
11121
11122
11123
11124
11125
11126
11127
11128
11129
11130
11131
11132
11133
11134
11135
11136
11137
11138
11139
11140
11141
11142
11143
11144
11145
11146
11147
11148
11149
11150
11151
11152
11153
11154
11155
11156
11157
11158
11159
11160
11161
11162
11163
11164
11165
11166
11167
11168
11169
11170
11171
11172
11173
11174
11175
11176
11177
11178
11179
11180
11181
11182
11183
11184
11185
11186
11187
11188
11189
11190
11191
11192
11193
11194
11195
11196
11197
11198
11199
11200
11201
11202
11203
11204
11205
11206
11207
11208
11209
11210
11211
11212
11213
11214
11215
11216
11217
11218
11219
11220
11221
11222
11223
11224
11225
11226
11227
11228
11229
11230
11231
11232
11233
11234
11235
11236
11237
11238
11239
11240
11241
11242
11243
11244
11245
11246
11247
11248
11249
11250
11251
11252
11253
11254
11255
11256
11257
11258
11259
11260
11261
11262
11263
11264
11265
11266
11267
11268
11269
11270
11271
11272
11273
11274
11275
11276
11277
11278
11279
11280
11281
11282
11283
11284
11285
11286
11287
11288
11289
11290
11291
11292
1129

simplified.

[0047] In addition, the invention is based on the task to provide a method for the determination of one or more analytes in one or more samples, allowing for the analysis of a multitude of samples within short time, i.e., economically, and without the necessity of additional tedious system adjustments between sequential individual measurements. According to the invention, this is made possible by the arrangement of large gratings with high precision, especially of gratings with long lines parallel to each other, additionally providing freedom for the design of the geometrical arrangement of the gratings, which is simple and economic at the same time.

[0048] It is preferred that the extension of said coupling grating along said line is at least 1 cm. It is further preferred that the coupling angle (θ) varies by not more than $0.05^\circ/\text{cm}$ along said line.

[0049] Furthermore, it is preferred that the absolute value of the deviation of the coupling angle (θ) from its average value on the waveguide plate does not exceed 0.3° , preferably not 0.15° .

[0050] Preferably, the refractive index of the waveguiding layer (2) is between 1.65 and 2.8. The waveguiding layer (2) can comprise, for example, Ta_2O_5 , Nb_2O_5 , TiO_2 , ZrO_2 , Al_2O_3 , $\text{SiO}_2\text{-TiO}_2$, HfD_2 , Y_2O_3 , SiONy , Si_3N_4 , HfOxNy , AlOxNy , TiOxNy , MgF_2 or CaF_2 . The thickness of the waveguiding layer is preferably between 50 nm and 200 nm. It is advantageous if the groove / land ratio of the at least one coupling grating is between 0.3

: 1 and 3 : 1, preferably between 0.7 : 1 and 1.5 : 1. It is preferred additionally, that the grating depth of the at least one coupling grating is between 5 nm and 75 nm.

[0051] For many applications, it is advantageous, if the at least one coupling grating covers only a part of the surface of the waveguide plate, whereas a residual part of the surface of the waveguide plate is uncovered. Thereby, it is especially preferred, that the waveguide plate is provided with at least one coupling grating, which is formed as a coupling grating strip (3), with lines parallel to one another extending essentially over the whole width or length of the waveguide plate.

Thereby, preferably several coupling gratings are arranged separate and parallel to each other.

[0052] The waveguide plate according to the invention can be modified in multiple ways without deviating from the basic idea of the invention. For example, also variable gratings, for example with a variable inter-grating line distance, can be manufactured and be provided as coupling gratings on the waveguide plate.

[0053] Also concerning the geometrical arrangement of the coupling gratings, there are further embodiments of the waveguide plate according to the invention, which can be advantageous for specific applications.

[0054] For example, several coupling gratings of a waveguide plate according to the invention must not be arranged in parallel to each other, but can also, for example, be arranged orthogonally (normal) to

each other. Two or more coupling gratings can also be superimposed. For other specific applications, it is preferred that the coupling gratings are mono-diffractive. For specific applications, for example for the incoupling of excitation light of different wavelengths from multiple light sources into the waveguiding layer (2), however, it can be advantageous, if one or more coupling gratings are multi-diffractive.

[0055] In a preferred embodiment of the waveguide plate according to the invention a coupling grating covers essentially the whole surface of said waveguide plate. It has to be understood that, in this preferred embodiment, for example boundary areas on the waveguide plate and / or areas between larger parts provided with a coupling grating (with an area of the order of square centimeters) can be free from coupling gratings.

[0056] It is characteristic for a waveguide plate according to the invention, that coupling gratings arranged on said waveguide plate are operable to incouple excitation light from one or more light sources into the waveguiding layer (2) and/or to outcouple light guided in the waveguiding layer (2).

[0057] Another subject of the invention is a specific sensor platform with a waveguide plate according to any of the embodiments disclosed above, wherein biological or biochemical or synthetic recognition elements for the specific recognition and/or binding of one or more analytes and / or for the specific interaction with said analytes are immobilized directly on the waveguiding layer (2) or by

means of an adhesion promoting layer additionally deposited on said waveguiding layer (2).

[0058] Thereby it is preferred that a multitude of similar or different biological or biochemical or synthetic recognition elements are immobilized in at least one array of discrete measurement areas directly on the waveguiding layer (2) or by means of an adhesion promoting layer additionally deposited on said waveguiding layer (2).

[0059] In the spirit of this invention, laterally separate ("discrete") measurement areas shall be defined by the closed area, which is occupied by the biological or biochemical or synthetic recognition elements immobilized thereon. These areas can have any geometry, for example the shape of spots, circles, rectangles, triangles, ellipses, or strips.

[0060] Similar to the waveguiding layer (2) and the glass substrate (1), an adhesion promoting layer, optionally deposited on the waveguiding layer (2), should be transparent at least in the spectral range of a launched excitation light and a luminescence light to be determined optionally. Thereby, said transparent spectral range can be between the ultraviolet and the infrared.

[0061] According to this invention, the term "luminescence" refers to the spontaneous emission of photons in the ultraviolet to infrared spectral range, after optical or not optical excitation, such as electrical or chemical or biochemical or thermal excitation.

Chemiluminescence, bioluminescence, electroluminescence and, especially, fluorescence and phosphorescence are included in the term "luminescence".

[0062] The adhesion promoting layer should not exceed the penetration depth of the evanescent field from the waveguiding layer (2) into the medium located thereon. For example, the adhesion promoting layer can have a thickness of less than 200 nm, preferably of less than 20 nm.

[0063] An adhesion promoting layer deposited on the waveguiding layer (2) preferably comprises a chemical compound from the groups comprising silanes, functionalized silanes, epoxides, functionalized, charged or polar polymers and "self-organized passive or functionalized mono- or multi-layers".

[0064] Preferred is an embodiment of a sensor platform according to the invention, wherein, as said biological or biochemical or synthetic recognition elements, components from the group formed by nucleic acids (such as DNA, RNA, oligonucleotides) and nucleic acid analogues (such as PNA, "peptide nucleic acids"), proteins, especially mono- and polyclonal antibodies, peptides, enzymes, aptamers, synthetic peptide structures, soluble membrane-bound and from membrane isolated proteins, such as membrane receptors, their ligands, antigens for antibodies, "histidin-tag components" and their complex forming partners, cavities generated by chemical synthesis to host molecular imprints are immobilized directly on the waveguiding layer (2) or by means of an

adhesion promoting layer additionally deposited on said waveguiding layer (2).

[0065] As the latter type of recognition elements, cavities have to be understood which are formed by a method described in the literature as "molecular imprinting". Following this method, the analyte or an analogue of the analyte, typically in organic solution, is encapsulated in a polymeric structure. It is then called an "imprint". Then, upon application of adequate reagents, the analyte or its analogue is dissolved from the polymeric structure again, leaving back an empty cavity. In a later analysis method, this empty cavity can be used as a binding site with high steric selectivity.

[0066] Also whole cells, cell components, cell membranes or their fragments can be immobilized as biochemical or biological recognition elements.

[0067] In many cases, the detection limit of an analytical method is limited from signals resulting from so-called nonspecific binding, which signals are caused by binding of the analyte or of other components applied for the determination of the analyte not only in the regions of the immobilized biological or biochemical or synthetic recognition elements, but to other regions free from these recognition elements, for example caused by hydrophobic adsorption or electrostatic interactions.

[0068] Therefore, it is advantageous when areas between the immobilized biological or biochemical or synthetic recognition elements

on the waveguiding layer (2) or on the adhesion promoting layer additionally deposited on the waveguiding layer (2) and /or between the laterally separated measurements areas are "passivated", for a minimization of nonspecific binding of analytes or of tracer compounds for said analytes, wherein compounds which are "chemically neutral" towards the analyte are deposited in said intermittent areas, comprising preferably compounds from the groups comprising albumins, especially bovine serum albumin or human serum albumin, casein, nonspecific polyclonal or monoclonal, alien-characteristic or empirically nonspecific antibodies for an analyte to be determined (especially for immunoassays), detergents - such as Tween 20 -, synthetic or natural lipids, fragmented natural or synthetic DNA, such as extracts from herring or salmon sperm, that do not hybridize with polynucleotides to be analyzed (especially for polynucleotide hybridization assays), or also comprising hydrophilic polymers, such as polyethylen glycols or dextrans.

[0069] It is preferred that a waveguide plate, respectively a sensor platform according to the invention is provided with an arrangement of preferably essentially closed sample compartments, for receiving one or more liquid samples to be analyzed. Subject of the invention thereby is an arrangement of one or more sample compartments, comprising a waveguide plate or a sensor platform according to the invention as a base plate and comprising a body combined with said base plate in such a way, that one or more spatial recesses are formed between the base plate and said body, for generation of one or more flow cells, each with at least one inlet and at least one outlet, which flow cells are fluidically sealed against each other.

[0070] Preferred is an arrangement of sample compartments in a 1- or 2-dimensional array, comprising a waveguide plate or a sensor platform according to the invention as a base plate and comprising a body combined with said base plate in such a way, that an array of spatial recesses is formed between the base plate and said body, for generation of an array of flow cells, each with at least one inlet and at least one outlet, which flow cells are fluidically sealed against each other.

[0071] In a specific embodiment of an arrangement of sample compartments according to the invention, spatial structures with the geometry of the footprint of the array of flow cells to be generated are formed on the waveguide plate or the sensor platform as the base plate.

[0072] It is preferred that recesses are formed in said body, for generation of the spatial recesses between the waveguide plate or the sensor platform as the base plate and said body to be combined with said base plate.

[0073] For an easier manufacturing, it can be advantageous, if the body to be combined with the waveguide plate or the sensor platform as the base plate is formed from several parts, wherein the combined parts of said body preferably form an irreversibly combined unit.

[0074] Thereby, it is preferred that the body combined with the waveguide plate or the sensor platform as the base plate is provided with means facilitating the combination of said body with the base plate.

[0075] An arrangement of sample compartments according to the invention can comprise, for example, 2 - 2000, preferably 2 - 400, still more preferably 2 - 100 flow cells.

[0076] It is preferred that the pitch (geometrical arrangement in rows and/or columns) of the inlets of the flow cells does correspond to the pitch (geometrical arrangement) of the wells of an industrial standard plate.

[0077] A specific embodiment of an arrangement of sample compartments according to the invention is related to, for example, 2 to 12 sample compartments in a column or, for example, 2 to 12 sample compartments in a row, which themselves are combined with a carrier ("meta-carrier") with the dimensions of industrial standard plates in such a way, that the pitch (geometrical arrangement in rows and/or columns) of the inlets of the flow cells does correspond to the pitch (geometrical arrangement) of the wells of an industrial standard plate.

[0078] It can be advantageous for many applications, for example in the course of nucleic acid hybridization assays with denaturation steps at elevated temperature (e.g. up to 80°C), if the arrangement of sample compartments according to the invention is closed with an additional covering top, for example a film, a membrane or a cover plate. Thereby, for example, an evaporation of liquid from the inlet and outlet openings of the sample compartments can be avoided.

[0079] In an arrangement of sample compartments according to the

invention, the inner volume of each flow cell can typically be $0.1 \mu\text{l}$ - $1000 \mu\text{l}$, preferably $1 \mu\text{l}$ - $20 \mu\text{l}$.

[0080] It is preferred that the depth of the recesses between the waveguide plate or the sensor platform as the base plate and the body combined with said base plate is $1 - 1000 \mu\text{m}$, preferably $20 - 200 \mu\text{m}$.

[0081] The base areas of the recesses between the waveguide plate or the sensor platform as the base plate and the body combined with the base plate are typically $0.1 \text{ mm}^2 - 200 \text{ mm}^2$, preferably $1 \text{ mm}^2 - 100 \text{ mm}^2$ each, wherein the size of the recesses of an array can be equal or different, and wherein the base areas can have any geometry, preferably rectangular or polygonal or also other geometry.

[0082] It is characteristic for an arrangement of sample compartments according to the invention, that the materials of the body combined with the waveguide plate or the sensor platform, as the base plate, and of an optional additional covering top are selected from the group of formable, moldable or millable plastics, metals, silicates, such as glass, quartz or ceramics.

[0083] Further embodiments of adequate arrangements of sample compartments are described in PCT/EP 00/ 12668. In combination with a waveguide plate according to the invention, the arrangements of sample compartments described therein are another subject of this invention.

[0084] A further subject of the invention is an optical system for

the determination of one or more luminescences with

at least one excitation light source

a waveguide plate or a sensor platform or an arrangement of sample compartments according to the invention, respectively, and

at least one detector for determination of the light emanating from the waveguide plate or the sensor platform and from measurements areas that might be located thereon.

[0085] In an embodiment of an optical system according to the invention, the excitation light is launched in a direct illumination or transmission illumination light configuration towards the measurement areas.

[0086] It is preferred that the detection of the luminescence light is performed in such a way that excitation light or luminescence light outcoupled by a coupling grating is detected as well.

[0087] In a preferred embodiment of the optical system, the excitation light emitted by the at least one light source is essentially parallel and is launched, at the resonance angle for incoupling by a coupling grating into the waveguiding layer (2), onto a coupling grating of the waveguide plate or the sensor platform or the arrangement of sample compartments.

[0088] As an "essentially parallel" light bundle, it shall be understood that its convergence or divergence are less than 1 degree. Correspondingly, "essentially orthogonal" or "essentially normal" shall

mean a deviation from a corresponding orthogonal or normal direction by less than 1 degree.

[0089] For most embodiments (except for those based on the use of a polychromatic light source), it is also preferred that the excitation light is essentially monochromatic. As "essentially monochromatic" light shall be understood, that its bandwidth is less than 1 nm.

[0090] Furthermore, it is preferred, that the excitation light is launched linearly polarized, for excitation of a TE_0 - or TM_0 -mode guided in the waveguiding layer (2).

0991614
[0091] For specific applications it is preferred that two or more light sources with similar or different emission wavelengths are used as excitation light sources. Preferably, these are coherent light sources.

072704
[0092] Characteristic for a specific embodiment of the optical system according to the invention is, that the excitation light of at least one light source is expanded by an expansion optics to an essentially parallel ray bundle and directed on one or more measurement areas on a coupling grating, which is preferably performed under the resonance angle for incoupling into the waveguiding layer (2).

[0093] Characteristic for another specific embodiment is, that the excitation light from the at least one light source is divided, by means of one or, in case of several light sources, multiple diffractive optical elements, preferably Dammann gratings, or refractive optical

curved mirrors for the deviation and optionally additional shaping of the light bundles, prisms for the deviation and optionally spectral separation of the light bundles, dichroic mirrors for the spectrally selective deviation of parts of the light bundles, neutral density filters for the regulation of the transmitted light intensity, optical filters or monochromators for the spectrally selective transmission of parts of the light bundles, or polarization selective elements for the selection of discrete polarization directions of the excitation or luminescence light can be located in the optical path between the one or more excitation light sources and a component of the group of components formed by a waveguide plate, a sensor platform, and an arrangement of sample compartments according to any of the embodiments described above, and/or in the optical path between said group of components and the one or more detectors.

[0098] Characteristic for a specific embodiment according to the invention is that the excitation light is launched in pulses with a duration between 1 fsec and 10 minutes, and that the emission light from the measurement areas is measured time-resolved.

[0099] Preferably, for referencing purposes, light signals of the group comprising excitation light at the location of the light sources or after expansion of the excitation light or after its multiplexing into individual beams, scattered light at the excitation wavelength or emission light at a wavelength different from the one used for analyte detection, from the location of the one or more laterally separated measurement areas, and light of the excitation wavelength outcoupled by

a coupling grating aside of the measurement areas, are measured.

[0100] Thereby, it is of special advantage if the measurement areas for determination of the emission light and of the reference signal are identical.

[0101] Launching of the excitation light and detection of the emission light from the one or more measurement areas can be performed simultaneously or sequentially for one or more measurement areas.

[0102] Preferably, sequential excitation and detection is performed using movable optical components of the group comprising mirrors, deviating prisms, and dichroic mirrors.

[0103] Thereby, it is characteristic for a specific embodiment of an optical system according to the invention, that sequential excitation and detection is performed using an essentially focus and angle preserving scanner.

[0104] In another method for sequential excitation and detection of the emission from one or more measurement areas, the waveguide plate or sensor platform or arrangement of sample compartments is moved between steps of sequential excitation and detection.

[0105] Another subject of the invention is a method for the simultaneous qualitative and/or quantitative determination of a multitude of analytes, with a component of the group of components

formed by a waveguide plate according to the invention and a sensor platform according to the invention and an arrangement of sample compartments according to the invention, and/or upon use of an optical system according to the invention, each according to any of the embodiments described above, wherein one or more liquid samples, to be analyzed for said one or more analytes, are brought into contact with the measurement areas on one of said components, excitation light is launched towards the measurement areas, and wherein at least one of (A) light emanating from the measurement areas and (B) optionally one or more luminescences from the measurement areas brought into contact with said sample or said samples, resulting from the binding of one or more analytes to the biological or biochemical or synthetic recognition elements immobilized in said measurement areas or from the interaction between said analytes and said immobilized recognition elements, are measured, wherein said luminescences are generated in the near-field of the waveguiding layer (2).

[0106] Again, it is preferred that the excitation light is essentially monochromatic and launched essentially in parallel. It is especially advantageous, if the excitation light is launched linearly polarized, for excitation of a TE_0 - or of a TM_0 -mode guided in the waveguiding layer (2).

[0107] It is especially preferred for many embodiments of the method according to the invention if the excitation light from at least one light source is expanded as homogeneously as possible to an essentially parallel ray bundle by a beam expansion optics and directed onto the one

or more measurement areas. Thereby, it is preferred that the diameter of the launched excitation light bundle is at least 2 mm, preferably at least 10 mm, in at least one direction.

[0108] Characteristic for another embodiment of the method according to the invention is, that the excitation light from the at least one light source is divided, by means of one, or in case of several light sources, by means of multiple diffractive optical elements, preferably Dammann gratings, or refractive optical elements, preferably micro-lens arrays, into a multitude of individual beams, with as similar intensity as possible of the individual beams originating from a common light source, which individual beams are directed essentially in parallel to each other onto laterally separated measurement areas.

[0109] In another embodiment of a method according to the invention it is preferred, that two or more coherent light sources with equal or different emission wavelength are used as excitation light sources.

[0110] Thereby, it is preferred that the excitation light for the measurement areas is coupled into the waveguiding layer (2) by means of one or more coupling grating.

[0111] The analysis method according to the invention allows for measuring (a) the isotropically emitted luminescence or (b) luminescence that is incoupled into the waveguiding layer (2) and outcoupled by a coupling grating, or for measuring luminescence comprising both parts (a) and (b) simultaneously.

[0112] Characteristic for the method, according to the invention, is also that for the generation of said luminescence, a luminescent dye or a luminescent nano-particle is used as a luminescence label, which can be excited and emits at a wavelength between 300 nm and 1100 nm.

[0113] Characteristic for a preferred embodiment of the method, according to the invention, is that the luminescence label is bound to the analyte or, in a competitive assay, to an analog of the analyte or, in a multi-step assay, to one of the binding partners of the immobilized biological or biochemical or synthetic recognition elements or to the biological or biochemical or synthetic recognition elements.

[0114] Characteristic for a specific embodiment is that a second or still more luminescence labels with similar or different excitation wavelength as the first luminescence label and with similar or different emission wavelength are used.

[0115] Thereby it is preferred that the second or still more luminescence labels can be excited at the same wavelength as the first luminescence label, but emit at different wavelengths than the first luminescence label.

[0116] On the other hand, it is advantageous for specific applications, if the excitation and emission spectra of the applied luminescence labels do not overlap or do overlap only little.

[0117] Characteristic for another specific embodiment of the

analysis method according to the invention is, that charge transfer or optical energy transfer from a first luminescence label acting as a donor to a second luminescence label acting as an acceptor are used for analyte determination.

[0118] For example for a reduction of the contribution of background signals at the excitation wavelength to the detected measurement signal it can be advantageous, if the one or more luminescences and/or determinations of light signals at the excitation wavelength are determined with selectivity of polarization, wherein preferably the one or more luminescences are measured at a polarization that is different from the polarization of the excitation light.

[0119] Characteristic for another specific embodiment of an analysis method according to the invention is, that changes of the effective refractive index on the measurement areas are determined in addition to the determination of one or more luminescences.

[0120] This modification, as a combined method of a determination of the effective refractive index and of a laterally resolved luminescence measurement, allows, for example, for a detection of the binding of a ligand, as the analyte, to a biological or biochemical or synthetic recognition element, as the receptor, being immobilized in one or more measurement areas, by means of a change of the effective refractive index, and for a determination of a functional response of said ligand-receptor system, by means of a change of the luminescence from said measurement areas.

[0121] The receptor-ligand system can, for example, be a transmembrane receptor protein, with a ligand in a supplied sample binding to said transmembrane receptor protein. A functional response of this receptor-ligand system can, for example, be the opening of an ion channel, leading to a local change of pH or/and of the ion concentration. Such a local change can for example be detected by means of a luminescent dye with a pHdependent or/and ion-dependent luminescence intensity and/or spectral emission.

[0122] The analysis method according to the invention, according to any of the embodiments disclosed above, is suited for the simultaneous or sequential, quantitative and/or qualitative determination of one or more analytes from the group comprising antibodies or antigens, receptors or ligands, chelators or "histidin-tag components", oligonucleotides, DNA or RNA strands, DNA or RNA analogues, enzymes, enzyme cofactors or inhibitors, lectins and carbohydrates.

[0123] Characteristic for the method, according to the invention, is that the samples to be examined are, for example, aqueous solutions, such as, in especial, buffer solutions, naturally occurring body fluids, such as blood, serum, plasm, lymph or urine, or egg yolk or optically turbid liquids or tissue fluids or surface water or soil or plant extracts or bio- or synthesis broths, or are taken from biological tissue fragments or cell cultures or cell extracts.

[0124] Another subject of the invention is the use of a component from the group of components formed by a waveguide plate according to

the invention, a sensor platform according to the invention, and an arrangement of sample compartments according to the invention, and / or of an optical system according to the invention, and/or of a method according to the invention, for quantitative and/or qualitative analyses for the determination of chemical, biochemical or biological analytes in screening methods in pharmaceutical research, combinatorial chemistry, clinical and preclinical development, for real-time binding studies and the determination of kinetic parameters in affinity screening and in research, for qualitative and quantitative analyte determinations, especially for DNA- and RNA analytics, for the generation of toxicity studies and the determination of gene or protein expression profiles and for the determination of antibodies, antigens, pathogens or bacteria in pharmaceutical product development and research, human and veterinary diagnostics, agrochemical product development and research, for patient stratification in pharmaceutical product development and for the therapeutic drug selection, for the determination of pathogens, nocuous agents and germs, especially of salmonella, prions, viruses and bacteria, in food and environmental analytics.

Example 1: Design of a waveguide plate according to the invention and arrangement of sample compartments to be formed by the combination with said waveguide plate

[0125] The waveguide plate according to the invention (Figures 1, 2 are schematically and not according to scale) comprises a glass substrate, for example of glass AF 45 from Schott DESAG, with dimensions of 102 mm x 72 mm and a thickness of 0.7 mm, carrying on one surface a waveguiding layer 2 of Ta_2O_5 of 150 nm thickness. The refractive index is,

dependent on the manufacturing method, for example 2.11 at 633 nm.

Besides Ta_2O_5 , also other materials are suited for the waveguiding layer, especially Nb_2O_5 , TiO_2 , ZrO_2 , Al_2O_3 , SiO_2-TiO_2 , HfO_2 , Y_2O_3 , SiO_xN_y , Si_3N_4 , HfO_xN_y , AlO_xN_y , TiO_xN_y , MgF_2 or CaF_2 .

[0126] On the surface carrying the waveguiding layer 2, several coupling grating strips 3 are arranged in parallel to and separate from each other, extending in parallel lines over the whole width of the waveguide plate. The width of each of the coupling grating strips 3 is 0.5 nm. The grating period is $\Lambda = 360$ nm, the groove / land ratio is about 1: 1, the grating depth about 20 nm. The parameters defining the grating are always fulfilled very precisely along the full length of the coupling grating strip. Thereby, changes of the coupling angle θ , at which angle a light ray, directed from beneath towards the coupling grating strip 3 through the glass substrate 1, is coupled into the waveguiding layer 2 with maximum coupling efficiency, are kept in very narrow limits. Along the lines of a coupling grating strip 3, the coupling angle changes by not more (at maximum by) $0.05^\circ/cm$. On the whole of the coupling angle from the mean value, which is 2.31° in the described example, is below 0.15° .

[0127] As shown in Fig. 3 and indicated in Fig. 1, the waveguide plate is accomplished by a honeycombed head piece 4, for example of plastics, to form an arrangement of sample compartments, for example with the footprint of an industrial standard plate.

[0128] If the content of a cavity 8 shall be examined for the

concentration of certain molecules, an adjacent coupling grating strip 3 of the waveguide plate 2 is illuminated with light from an adequate light source under the coupling angle θ , principally in a known matter, in this example from a He-Ne laser with light of a wavelength of 633 nm. The light guided through the waveguiding layer 2, forming the base (bottom) of the cavity 8, which is guided in this example, not limiting the general aspects of the invention, towards an adjacent coupling grating strip 3' and being outcoupled there again, does excite molecules in the cavity 8 to fluorescence which is detected by an optical system 9 and can then be analyzed. The high precision, within which the coupling angle θ can be guaranteed along the length of the coupling grating strip 3, allows for a simultaneous analysis of the cavities arranged along said coupling grating strip with high efficiency. The coupling angle θ deviating only little from the average value over the whole waveguide plate 2, for the analysis of the next row of cavities 8 a tedious optimization of said coupling angle is also not necessary.

Example 2: Characterization of a waveguide plate according to the invention

[0129] A waveguide plate according to Example I (waveguiding layer of Ta_2O_5 , refractive index $n = 2.11$ at 633 nm) is characterized. The waveguide plate is designed for use as a base plate for an arrangement of 96 sample compartments (provided as flowthrough cells) in a geometrical arrangement according to Fig. 1 (8 rows x 12 columns of sample compartments). For the characterization of the physical properties of the waveguide plate, the following parameters shall be determined: (a) coupling angle and (b) the halfwidth of the resonance angle for maximum

incoupling, (c) the lateral position ("x-position") for optimum incoupling on a coupling grating strip and (d) its halfwidth, (e) the incoupling efficiency, (f) the number and size of scattering centers per area unit of the region of the sample compartments, analysis of (g) the excitation light profile for the region of the sample compartments, (h) background luminescence at the wavelength of the luminescence measurement for an analyte determination to be performed later on.

[0130] In this example, the interval for the launching of excitation light and determination of the measurement light emanating from measurement positions for sample compartments in adjacent rows and columns is 9 mm.

Optical system for the characterization

[0131] The optical system for the determination of the parameters for the characterization of a waveguide plate comprises three lasers, or laser diodes as alternative excitation light sources, with emission at 635 nm, 532 nm, and 492 nm. The excitation light from the different lasers is directed onto the coupling gratings of the waveguide plate by means of a system of lenses, apertures (for beam shaping) and mirrors. The last mirror in the excitation light path, before the light hitting the waveguide plate, is mounted on a goniometer (resolution 0.01° in this example), in order to allow for a precise adjustment of the coupling angle or for a deviation of the excitation light for the determination of the total excitation light intensity (I_0) launched onto the waveguide plate, and of the sum of the intensity of the reflected and immediately outcoupled excitation light (I_r , in parallel to the reflected light). The

adjustment of the lateral position of the launching of the excitation light onto the waveguide plate (x: normal to the coupling grating strips; y: in parallel to the coupling grating strips) is performed by moving the waveguide plate by means of translational positioning elements (resolution 20 microns in this example).

[0132] The adjustment for maximum incoupling is performed by maximizing the signal of a photodiode (connected to an amplifier) measuring the light outcoupled at the next coupling grating, with respect to the direction of propagation of the light incoupled into the waveguiding layer. During that optimization, the intensities of the outcoupled light (I_{out}) are measured by the photodiode as a function of the incoupling angle (defined as the angle with respect to the normal of the waveguide plate), within an adjustment range and with a variable resolution, which can both be defined by the user. The optimum values for maximum incoupling and the halfwidths of the coupling curves (resonance curves) are then determined from these intensity profiles.

[0133] For the determination of the relative incoupling efficiency (ϵ), the intensity of the undiffracted light (I_{tr}), transmitted through the waveguide plate, the intensity of the launched excitation light (I_o), and of the sum (I_r) of the reflected light and of the light outcoupled at the incoupling grating (not distinguishable from the reflected light as being outcoupled in parallel to the reflected light) are measured with calibrated photodiodes (connected to amplifiers). The incoupling efficiency is determined as the ratio $(I_o - I_{tr} - I_r) / I_o$.

[0134] For the determination of the other characterization parameters (f) to (h), the light emanating from the range of interest on the waveguide plate is imaged onto a laterally resolving detector, such as a camera or a CCD-chip, by means of an imaging system (combination of objective lenses). The measurement for the determination of the parameters (f) and (g) is again performed at the actual excitation wavelength (using neutral density filters for attenuation of the light intensity if necessary, but without use of spectrally selective filters), whereas the background luminescence (h) is determined upon using an adequate interference filter, which is mounted in a rotatable filter wheel in the optical path for the collection of this measurement light.

[0135] For the determination of the (f) number and size of scattering centers, first an average value of the signal intensities (from all pixels) of the whole area of interest is determined from the image (taken at the excitation wavelength). Thereby, it has to be taken care that the region of the coupling grating or areas immediately adjacent to the coupling grating are not taken into account in this averaging process, and, of course, reflections reaching the detector have to be avoided. Then a threshold intensity is defined, which is significantly higher than the upper limit of the statistical variation around the average value (definable by the user, for example average value + its tenfold standard deviation). All pixel signals above this threshold value are attributed to scattering centers, and a table is generated, how many of these pixels in a (2-dimensional) continuous area have signals above this threshold value (size of the scattering centers). The complete analysis for scattering centers is then provided in the form of a "histogram" with the

number of scattering centers as a function of their size.

[0136] For the (g) determination of an excitation light profile of an area of interest on the waveguide plate, line profiles of the recorded pixel values of strip-like image sections of the corresponding areas on the waveguide plate (in y-direction, in parallel to the, grating lines) are generated. Based on these line profiles, it can be determined if, for example, no or reduced light incoupling does occur, because of defects of the coupling gratings at different sites, or if the propagation of the incoupled, guided light is interrupted or impaired (because of defects localized at sites further down in x-direction). Threshold values for the homogeneity (in y-direction; e.g. amount of the variation or relative deviation from the measured average value) of the measured intensity can be defined, the waveguide plate being discarded upon the occasion of their exceeding.

[0137] As mentioned, the background luminescence is determined upon using an adequate spectral filter for the actual luminescence wavelength of interest. Localized luminescent contaminations can be determined, for example in a manner similar to the analysis of scattering centers, and also integral luminescence intensities of all pixel values relevant for the analysis of the whole area of interest can be determined. Preferably, the measured values are corrected or referenced, respectively, with the available excitation light intensities, in order to allow for an empiric comparison between comparable waveguide plates. Similar as for all parameters mentioned above, again threshold values can be defined, a waveguide plate being discarded upon an exceeding or

, failing below these threshold values.

[0138] Preferably, all steps of the characterization of a waveguide plate are performed completely automatically resp. computer-controlled. It is especially preferred that a protocol is generated, comprising, for example, tables and optionally graphic representations of the determined parameters. Preferably, the grading and categorization of the characterized waveguide plates is performed in an automated manner as well.

[0149] As an example for a partial result of the characterization of a waveguide plate according to the invention, the average values of the determined coupling angles for excitation at 635 nm and at 532 nm, measured along a coupling grating strip ("column"; averages of 8 measurement positions), and the maximum deviations ($\Delta_{\max-}$, $\Delta_{\max+}$) along a coupling grating strip ("column," distance between first and last measurement position of a column: 63 mm) are summarized in the following table.

[0140] Along all coupling grating strips (columns), the variation of the coupling angle for both wavelengths is below 0.1'/cm; on the whole from the average value is below 0.5°.

Column (coupling grating strip) No.	Excitation: 635 nm Coupling angle [°]			Excitation: 532 nm Coupling angle [°]		
	AVG	$\Delta_{\max-}$	$\Delta_{\max+}$	AVG	$\Delta_{\max+}$	$\Delta_{\max+}$
1	-13.39	-0.15	+0.28	11.72	-0.22	+0.27
2	-13.34	-0.15	+0.23	11.77	-0.20	+0.31
3	-13.26	-0.13	+0.22	11.84	-0.17	+0.26
4	-13.21	-0.11	+0.21	11.94	-0.22	+0.28
5	-13.13	-0.17	+0.29	12.00	-0.19	+0.31
6	-13.10	-0.18	+0.28	12.03	-0.20	+0.30
7	-13.08	-0.18	+0.27	12.07	-0.21	+0.27
8	-13.07	-0.16	+0.24	12.09	-0.23	+0.34
9	-13.06	-0.19	+0.29	12.08	-0.21	+0.27
10	-13.06	-0.16	+0.27	12.07	-0.21	+0.28
11	-13.08	-0.16	+0.28	12.05	-0.19	+0.28
12	-13.10	-0.15	+0.28	12.03	-0.20	+0.32
Whole plate	-13.15	-0.39	+0.38	11.98	-0.48	+0.45

Table 1: Average coupling angles on adjacent coupling grating strips ("columns") and maximum positive and negative deviation of the coupling angle along one coupling grating strip. Last row: Average values and maximum deviations on the whole waveguide plate.

[0141] If it is intended to investigate the contents of a cavity 8, for instance an analyte such as blood, serum, urine, saliva, or a solution containing a drug candidate, with respect to the concentration of specific molecules, an adjacent coupling grating 3 of the evanescent field sensor plate 2 is exposed in a manner known per se to a suitable light source at the coupling angle θ , the light having a specific wavelength, in the example to light with a wavelength of 633 nm, by means of a He-Ne laser. The light is conducted through the layer 2 forming the bottom of the of the cavity 8 to the adjacent coupling grating 3', and there coupled back out. The evanescent light stimulates fluorescence in molecules in the cavity 8 which are bound to recognition elements, which fluorescence is recorded by an optical system 9 and then

analyzed. The high precision with which the coupling angle θ is preserved over the length of the coupling grating 3 permits a simultaneous and highly efficient examination of the cavities arranged along the same. Since over the entire evanescent field sensor plate 2, the coupling angle θ departs but slightly from the mean value, no laborious optimization of this angle is required even when examining the next row of cavities 8. As an alternative or in addition to evaluating the fluorescence, one can also record changes in the refractive index produced at the bottom of cavity 8 by the binding of molecules to the recognition elements.

[0142] As shown schematically in Figs. 4a-e, to produce the transparent layer 2, one first applies a photoresist, e.g. AZ1518, diluted 1 : 4 with AZ1500, both of Clariant, at 1300 rpm to the substrate 1 and then bakes for 30 min at 90°C in an oven, whereupon Aquatar of the same manufacturer is applied at 1400 rpm and once again baked for 15 min at 90°C in the oven. The photoresist layer 10 thus produced has a thickness of less than 200 nm, as a rule of about 150 nm, so that interfering standing waves will not develop in it. The reflectivity is below 1%, so that interfering reflections which could lead to the development of Newton's rings are also practically excluded (Fig. 4a).

[0143] In a subsequent step, the photoresist layer 10 is exposed for 70 sec. For this purpose, the glass substrate 1 is introduced into a setup according to Fig. 5, a mask aligner MA4 from Stüss, Munich, which comprises a modified mercury vapour lamp 11 having a modified down-

circuit optical system 12 and deflecting mirror 13. The optical system 12 comprises a bandpass filter which, for example, filters out the I-line at a wavelength of 365 nm, and a polarizer, which preferably produces s-polarization. To improve the parallelism of the beams, the fly's eye is removed from the beam path and a lamp with as small an arc as possible is used and is positioned as far away from the substrate as possible.

[0144] The exposure is performed through a phase mask 14. It comprises a substrate of a transparent material, in the example quartz, with a diffraction grating which carries a structured layer of nontransparent material, in the example chromium, which in this case is interrupted by strips following one another at regular intervals. Phase masks of this type and are manufactured approximately as follows:

[0145] A quartz substrate 15 is covered with a photoresist layer 16 (Fig. 7a) and the latter is exposed to light by the two-beam interference method and developed (Fig. 7b). Such structure can be obtained from Ibsen in Farum (Denmark). Thereafter, a diffraction grating is produced on the surface of the quartz substrate 15 by etching and subsequent removal of the photoresist over the whole area (Fig. 7c). Said surface is then completely covered with a chromium layer 17 (Fig. 7d). A continuous photoresist layer 18 is then applied to the chromium layer 17 (Fig. 7e) and exposed through a mask structured by inscribing by-means of electron or laser beams. The photoresist is then developed (Fig. 7f) and the chromium layer 17 is removed by etching from the parts not covered by photoresist. Finally, the residues of the photoresist

layer 18 are removed to complete the phase mask 14 (Fig. 7g). The structure of the mask thus determines which parts of the phase mask are transparent.

[0146] The substrate 1 is arranged underneath the phase mask 14 in such a way that the photoresist layer 10 is in vacuum contact with said phase mask. The upper side of the phase mask 14 is exposed at an angle which corresponds approximately to the Lithrow angle θ_L at which the angle of incidence is equal to the angle of first order diffraction, in particular deviates by not more than 10° , preferably not more than 5° , from that angle. Under these conditions, a pronounced diffraction pattern whose structure corresponds to that of the grating of the phase mask 14 forms in the vicinity below the transparent regions of the phase mask 14 (Fig. 6). Alternatively, the phase mask 14 can also be exposed at an angle which approximately corresponds to a right angle, in particular deviates therefrom by not more than 10° , preferably not more than 5° (deflecting mirror 131 shown as a dashed line). In this case, the diffraction pattern in the vicinity of the phase mask 14 has half the period of the grating thereof.

[0147] After exposure the Aquatar layer is removed by washing with deionized water, and the photoresist is then developed (Fig. 4b). Those parts of the surface of substrate 1 which are not covered with photoresist are then etched with Ar and CHClF_2 at a pressure of 0.2 mbar in a parallel-plate reactor with capacitive excitation of the plasma at 13.6 MHz and an RF power of 50 W. The etch depth is 20 nm. The photoresist is then removed. For this purpose, it is first subjected to

reactive ion etching for 60 s in an oxygen plasma at a pressure of 0.2 mbar and an RF power of 50 W, then detached with Remover AZ100, Deconex, and deionized water (Fig. 4d).

[0148] Finally the layer 2 is applied by reactive pulsed DC magnetron sputtering or by DC magnetron sputtering superimposed with an AC frequency between 1 kHz and 1 MHz, in a Balzers MSP1000 unit, similarly as described in EP-A-0 508 359 (Fig. 4e). This step is carried out in an Ar-O₂ atmosphere at a pressure of 3.7 μ bar. The target material is tantalum. Finally, the evanescent field sensor plate or waveguide plate respectively is cut to its final size by wafer sawing.

[0149] Particularly on account of exposure through a phase mask that can be reused practically as often as desired, the process described permits the production of elements with grating structures, particularly diffractive coupling gratings, in large numbers and in a simple manner. The fact that the phase mask is structured by the two-beam interference method also implies that large defect-free grating, structures having surface areas of 10 cm² and more can be produced on it with high precision, whereas other structuring methods such as electron beam writing are not suitable for this purpose owing to their virtually unavoidable stitching errors. Therefore, large optical, elements with large-area gratings of high quality and uniformity can be produced, not only as final products but also as semifinished plates which by wafer sawing, scribing and breaking or laser cutting can then be separated into smaller final products which thus can be produced very economically and in high quality.

[0150] Evanescent field sensor plates or waveguide plates respectively can of course also be produced in geometries and optical properties corresponding to other standards or requirements. Thus, another evanescent field sensor plate or waveguide plate respectively can have dimensions of 57 mm x 14 mm x 0.7 mm and be provided with two strip-shaped coupling gratings having a width of 0.5 mm each which are symmetrically arranged in parallel with the long sides, and have a mutual distance of 9 mm. The grating period $A = 318$ nm, the grating depth 12 nm, while otherwise the properties of the layer and coupling gratings are the same as in the first example. In this case the coupling angle $\theta = -12.14^\circ$ at a wavelength of 633 nm, varying parallel to the x -axis by at most $0.15^\circ/\text{cm}$. The deviation from a mean value remains below 0.05° everywhere on the evanescent field sensor plate or waveguide plate respectively. For the production of a semifinished plate from which the individual evanescent field sensor plates or waveguide plates respectively are then obtained by wafer sawing, a phase mask is employed which measures 150 mm x 150 mm and has a region with a grating of grating period 318 nm measuring 115 mm x 115 mm. The regions corresponding to the coupling gratings are bare while the remaining portion of the grating is again masked by a nontransparent layer, particularly a chromium layer. Otherwise the production proceeds as described above.

[0151] A further example is an evanescent field sensor plate or waveguide plate respectively measuring 75 mm x 113.5 mm 0.7 mm which as to its basic features essentially corresponds to Fig. 1, and which bears 13 strip-shaped coupling gratings each 0.5 mm wide which are parallel to the broadside and have distances between neighboring strips of 8.5 mm

each. Layer and grating properties correspond to those of the second example. The coupling angle $\theta = -11.48^\circ$ at a wavelength of 633 nm, varying parallel to the lines by at most $0.05^\circ/\text{cm}$. Over the entire evanescent field sensor plate or waveguide plate respectively it departs from a mean value by at most 0.4° . The evanescent field sensor plate or waveguide plate respectively can be expanded to a microtitre plate or waveguide plate respectively with 8×12 cavities by adding a suitable top portion.

[0152] Apart from the embodiments of optical elements having grating structures produced by the process according to the invention and used in chemical analysis, as portrayed above, embodiments for applications in communications technology are particularly pertinent. Such elements are suited above all as highly efficient optical couplers such as those employed in fibre-optic networks.

[0153] A first example of such a coupler is represented in Figs. 8a and 8b. On a substrate 1 consisting of a glass plate 19 and a layer 20 of transparent material, a coupling grating 3 formed as a line grating of constant grating period is arranged. The layer 20 is covered by a transparent layer 2, consisting for instance of Ta_2O_5 . Layer 2 acts as a waveguide. The coupling grating 3 reflects light of a particular wavelength λ_B according to the wavelength-dependent reflectivity R schematically represented in Fig. 9a, while incident light of all other wavelengths is transmitted. This is shown in Figs. 9b-d, where Fig. 9a shows the incident wavelengths, Fig. 9b the reflected wavelength λ_B , and Fig. 9c the transmitted wavelengths. Using the coupler it is thus

possible to filter out a particular wavelength, for instance in a fibre-optic network using wavelength multiplexing. Thanks to the high grating quality, the full width at half maximum of the reflectivity R as a function of wavelength is very small. Hence even with wavelengths very closely spaced, it is possible to highly efficiently separate a wavelength.

[0154] An example for the use of such a coupler is shown in Fig. 10.

Two parallel stripe waveguides 21a, b of known structure are running parallel at a very small mutual distance in a coupling region 22, in such a way that 50% of the light conducted in the first stripe waveguide 21a is transferred to the second stripe waveguide 21b, and vice versa. In the final segment of the first stripe waveguide 21a, a coupler 23 with a coupling grating 3 according to Figs. 8a and b is incorporated which selectively reflects light having a wavelength λ_3 .

[0155] When signals having wavelengths $\lambda_1, \lambda_2, \lambda_3, \lambda_4$ etc. are fed into the first stripe waveguide 21a at an input 24, then on one hand 50% of all signals in the coupling region 22 are transferred to the second stripe waveguide 21b where they are conducted to a first output 25a, while the signals remaining in the first stripe waveguide 21a are conducted to a second output 25b, except for the signal of wavelength λ_3 corresponding to the λ_3 according to Figs. 9a-d which is reflected at the coupler 23 so that in the coupling region 22, 50% of its intensity transfer into the second stripe waveguide 21b where the signal is conducted in a direction opposite to that of the signals transferred directly from the first stripe waveguide 21a, and reaches a third output

25c where finally it has been isolated and can be further processed. The signals of outputs 2Sa and b can be recombined to a signal differing from the original one only by a 50 % attenuation of the signal with wavelength λ_3 .

[0156] The coupler 23 can be completely integrated into the first stripe waveguide 21a, in such a way that this has the same structure as coupler 23 and this coupler forms a single part with the first stripe waveguide 21a. The only distinction of coupler 23 is then its bearing the coupling grating 3.

[0157] A second example of a coupler is represented in Figs. 11a and 11b. In a longitudinal direction on top of a rectangular substrate 1 of glass, for instance Schott DESAG AF 45 with a refractive index of 1.52, two coupling gratings, an input coupling grating 3a and an output coupling grating 3b, are arranged consecutively at a mutual distance, each extending over the full width of the coupler. The input coupling grating 3a has a grating period of $\Lambda_1 = 981$ nm and a grating depth of 6 nm, the output coupling grating 3b has a grating period of $\Lambda_2 = 1350$ nm and a grating depth of 12 nm. The upper side of substrate 1 is covered by a continuous transparent layer 2 consisting of Ta_2O_5 and having a refractive index of 2.1. Its thickness is 400 nm.

[0158] The coupler can be used as a drop filter monitoring and stabilising the intensity of a light beam, for instance a line of a multimode laser. To this end (Fig. 12), the coupler 23 described above is so arranged between the ends of a first optical fiber 26a and a

second optical fiber 26b arranged in the continuation of the former that the input coupling grating 3a faces the end of the latter while the former faces the bottom side of coupler 23. The light supplied by the first optical fibre 26a passes through the part of the coupler 23 carrying the input coupling grating 3a while a fraction of the light of the 1550 nm line corresponding to less than 0.01% of its intensity is coupled into the layer 2 by said grating. At the output coupling grating 3b, light is coupled out at an angle of 30° and reaches an appropriately disposed photodetector the output signal of which is a measure of intensity of the monitored line. Owing to the high precision of the input coupling grating 3a, the input coupling is highly wavelength-sensitive, the full width at half maximum of the intensity distribution being a mere 0.01 nm, so that a specific monitoring of a single wavelength is possible even where the wavelengths are closely spaced, as desired in wavelength multiplexing in the interest of a high transmission capacity.

[0159] A third example of an optical coupler according to the invention is represented in Figs. 13a and b. A rectangular substrate 1 consists of a glass plate 19 with a refractive index of 1.586 and a transparent layer 20 of TiO_2 with a refractive index of 2.4 covering the upper face of this glass plate in a thickness of 285 nm. The upper face bears a coupling grating 3 occupying its full width which has been produced by removing layer 20 completely in a pattern of lines, and is covered by a further transparent layer 2 consisting of MgF_2 which is 342 nm thick and has a refractive index of 1.38. The grating depth thus corresponds to the thickness of layer 20, and is 285 nm. The grating period $\Lambda_{(x)}$ varies linearly in a direction normal to the grating lines,

increasing from $\lambda_1 = 970$ nm to $\lambda_2 = 977$ nm.

[0160] When producing the coupler, layers 20 and 2 can be applied as described in connection with the first example of an evanescent field sensor plate or waveguide plate respectively. Production of the coupling grating 3 after application of the layer 20 also occurs as described there. In this operation, a phase mask is used whose grating varies appropriately, hence linearly in the present case. Such phase masks can be produced by appropriately bending a flexible master copy and applying a grating structure using the two beam interference method.

The phase mask is derived by replication, that is, by making an impression of the reflattened master copy.

[0161] The coupler can advantageously be used in a device for monitoring and stabilising the wavelength of a laser 28 (Fig. 14) the light of which is fed into a light-conducting fibre 29, for instance a glass fibre, of a fibre network. The device comprises a semi-transmissive mirror 30 arranged in the path of the light beam coming from the laser 28, followed by a first optical system 31 to expand, and a second optical system 32 to collimate the part of the light beam deflected by the mirror 30. Following after the optical systems, the coupler 23 described above is arranged in the light beam normal to the beam direction, in such a way that the beam strikes the coupling grating 3. Mounted directly beneath the coupler 23 is a detector system with two photodetectors 33a and b which are arranged so as to be immediately adjacent one behind the other and normal to the lines in such a way that the part of the light beam transmitted by a first portion of the

coupling grating 3 where the grating period is between Λ_1 and an intermediate value Λ_i strikes the first photodetector 33a while the part transmitted by the remaining portion of the coupling grating 3 where the grating period is between Λ_i and Λ_2 strikes the second photodetector 33b. The photodetectors 33a and b can be displaced so that Λ_i is adjustable.

[0162] The transmissivity of the coupler 23 is a sensitive function of wavelength and of the grating period Λ . Because of the position-dependent variation of the grating period $\Lambda(x)$, therefore, it exhibits a specific wavelength dependence for the incident light which depends on its position. This is shown in Fig. 15, where the transmissivity T can be gathered as a function of position on the coupling grating 3 for three very close wavelengths (1549.5 nm, 1550 nm, 1550.5 nm). The minimum of the transmissivity curve shifts to larger or smaller grating periods as the wavelengths increase or decrease, and hence to a different position on the grating. This in turn gives rise to changes in the relative intensities of the light captured by the photo-detectors 33a and 33b, which has a direct affect on the size of their output signals I_a and I_b .

[0163] For the purposes of stabilizing a particular wavelength, one can then roughly adjust the position of the detector arrangement in accordance with the wavelength of interest, and then calculate a value

$$Q = (I_a - I_b) / (I_a + I_b)$$

and reduce it to zero by shifting the detector arrangement. Any change in wavelength of the light beam coming from the laser 28 will give rise to a positive or a negative deviation of the value of Q from zero,

depending on the direction of the wavelength change, and can be compensated by corresponding control of the laser 28. The intensity of the light beam is unimportant here. Only the intensity distribution of the expanded light beam which may not be homogeneous but follow a gaussian distribution, for instance, might eventually cause perturbations, but this can then be compensated by appropriate arrangement on extension of the optical systems or by calculation.

[0164] The optical elements according to the invention can be modified in many respects without departing from the basic concept of the invention. Thus, in many cases deviations from the mean value of up to 0.3° or even up to 0.5° over the entire element or even over a coupling grating can be admitted. For the evanescent field sensor plates and waveguide plates, too, it will often be sufficient when the changes in coupling angle θ along the grating lines are not larger than 0.1°/cm.

[0165] Many deviations or special adaptations to particular requirements are possible as well in the production process. Thus, even in the exposure step which is decisive for the process, the photoresist layer may be spaced apart from the phase mask, which facilitates the process. However, it must be arranged in the near field, that is, at a distance which as a rule is smaller than 100 μm , for the diffraction pattern to be sufficiently pronounced. This distance may perhaps be between 2 μm and 100 μm . Instead of a mercury-vapor lamp, a laser can also be used as the light source, particularly at excimer laser or an argon laser. Apart from Ta_2O_5 , other substances can be used as materials

for the layer, particularly Nb_2O_5 , TiO_2 , ZrO_2 , Al_2O_3 , $\text{SiO}_2\text{-TiO}_2$, HfO_2 , Y_2O_3 , SiO_xN_y , HfO_xN_y , AlO_xN_y , TiO_xN_y , MgF_2 oder CaF_2 . Ion-enhanced evaporation or plasma-enhances gas phase deposition can be used as coating methods. Finally, several layers differing in their composition and thickness can be applied consecutively, as described in one of the embodiments portrayed.

[0166] Phase masks need not be produced directly by the two-beam interference but can be copied directly or indirectly from a master copy thus produced. They can be used several times with layers interrupted in diverse manner when diverse arrangements of coupling gratings and the like are to be generated while maintaining a constant grating period. Instead of a nontransparent layer, a suitable layer of transparent material can also be used. Thus, the grooves of the grating can be filled by a material having the refractive index of the phase mask substance.

[0167] The phase mask can be antireflection-coated. In this case, it may not be necessary to apply a reflection-reducing layer to the photoresist layer, which facilitates the production of series of grating structures on the substrates. For antireflection, a layer having a refractive index between that of the phase mask substance and that of air, and for instance consisting of MgF_2 , is applied to the side of the phase mask facing the photoresist layer. At the same time, the grating must be adjusted in such a way that the interfering diffraction orders of the transmitted light will again have the same intensity. This adjustment can occur by changing the groove-to-land ratio and the

grating depth, which are readily calculated with the aid of programs known among experts.

[0168] The foregoing disclosure has been set forth merely to illustrate the invention and is not intended to be limiting. Since modifications of the disclosed embodiments incorporating the spirit and substance of the invention may occur to persons skilled in the art, the invention should be construed to include everything within the scope of the appended claims and equivalents thereof.

091514.072701
T072701.072701